

Description	Soft semi-closed cell EPDM foam with a pressure-sensitive adhesive on one side. Excellent space filling and air sealing capabilities, even under high strain conditions.
Cellular structure	Semi-closed cell extruded EPDM foam.
Color	Black
Density (ISO 2781)	90 ±15 kg/m <sup>3</sup>
Thickness EPDM	3mm to 30 mm
Compression Deflection (>8mm thickness) (ASTM D 1056)	<4 kPa @25% <6 kPa @50%
Compression Set (room temperature) 50% (ISO 1856)	≤25 %
Tensile strength (ISO 1798)	≥70 kPa
Tear Strength (ISO 34-1 method B)	≥ 0.4 kN/m
Elongation (according to ISO 1798)	100-250 %
Migration Staining (ASTM D925 Method B)	pass
Ozone resistance (ASTM D1149) (ASTM D1171)	Pass Pass
Accelerated aging, 7 days, 70 °C (ASTM D1056)	Bending without cracking
Fire performance (FMVSS - 302)	Pass
Adhesive type A	Modified acrylic adhesive
Total thickness	0.12 mm
Temperature resistance	From -40°C to +120°C (intermittent use)
Application	Designed for space filling and sealing against air, dust, noise and heat.
Compliant with	RoHS & REACH
Important instructions	The product must be stored in its original packaging in a clean, dry, well ventilated area.
Suggestions for disposal	It does not contain hazardous compounds such as cadmium, lead, CFCs, formaldehyde, etc. which require compliance to waste disposal regulations from 7/04/2009.

*The above given information has been provided by the producer and it should be considered as a guide. Given the variety of factors that can affect the use and performance of the product, user should evaluate to determine its suitability for purpose*